



Aluminium IR350

Characteristics

- Water atomised metal powder produced of pure aluminium min 99.5%.
- Particle shape : Irregular

Applications

- Suitable for all cold-cast metal applications.
- Particularly suitable for mould coating slurry of fine castings or 'cut' moulds.

Particle Size Distribution

BSS Mesh	Microns	%
350	>43	5%
-350	<43	95%

Chemical Analysis

Aluminium	: >99.5%
Apparent Density	: Approx 1 g/cm ³

Processing

ALUMINIUM IR350 may be used by simply dusting the mould or by adding the material to the casting resin to form a gel-coat on the mould.

Storage

Store in tightly closed containers in a cool dry environment. Store away from combustible materials or oxidising agents.

Safety Information

Comprehensive instructions are given in the corresponding material safety data sheets.

Technical Advice provided by MB Fibreglass - Either verbal, in writing or by way of trials - is given in good faith but without warranty, where proprietary rights of third parties are involved this applies also. This does not release you from the obligation to test the products supplied by us to ascertain their suitability for the intended processes and uses. The application, use, handling and processing of the products are outside of our control and therefore entirely your own responsibility