



T

Technical Data



TD01.14 FC1W/H Flocoat White Brushing

- Description** White standard brushing polyester flocoat.
- Intended Use** Designed as a white general purpose topcoat for use in GRP constructions to hide fibre from lamination and generally improve appearance.
- Characteristics** Suitable for application by brush or roller to give a tack free film.
- Application** Laminate surfaces may need abrading for best adhesion. Formulated to cure at temperatures > 16°C and needs only the addition of catalyst prior to use. Medium activity methylethyl ketone peroxide (MEKP) is the recommended catalyst at an addition level of 2% by weight to ensure sufficient cure at room temperature.

Properties of liquid flocoat

Appearance	White liquid
Liquid properties	Pseudoplastic and thixotropic
Gel time	100gm flocoat, 2% MEKP @ 25°C < 15 minutes

March 2004