

## **HEMPEL'S ANTI-SLINT 67500**

**Description:** HEMPEL'S ANTI-SLINT 67500 is flame dried silica sand of which the average particle size is

approximately 0.5 millimetres.

Recommended use: To obtain anti-skid properties on decks and other areas where a skid-proof surface is required.

Availability: Part of Group Assortment. Local availability subject to confirmation.

**PHYSICAL CONSTANTS:** 

Shade nos/Colours: 99980/ Greyish

Flash point: None.

Specific gravity: 2.6 kg/litre [21.9 lbs/US gallon]

Particle shape: Grit

VOC content: 0 g/l [0 lbs/US gallon]

The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.

**APPLICATION DETAILS:** 

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers,

consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.

**REMARKS:** Being heavy and rather coarse HEMPEL'S ANTI-SLINT 67500 should not be stirred into the paint

before its application. For such purpose use HEMPEL'S ANTI-SLIP BEADS 67420.

HEMPEL'S ANTI-SLINT 67500 should be sprinkled evenly on the surface immediately upon

application of the penultimate coat of the paint system while the paint is still wet.

Consumption approximately 2.5 kg/5.5 lbs of HEMPEL'S ANTI-SLINT 67500 to 25 sq.m/ 270 sq.feet.

When the paint is dry, sweep up surplus grit and apply the final coat.

Do not mix contaminated sweepings with new supplies.

Storage Conditions: Store under dry and clean conditions.

HEMPEL'S ANTI-SLINT 67500 For professional use only. Note:

ISSUED BY: HEMPEL A/S 6750099980

This Product Data Sheet supersedes those previously issued.
For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

Froducts are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.



Date of issue: February 2014 Page: 1