



## HEMPEL'S WOOD IMPREG 02360

**Description:** HEMPEL'S WOOD IMPREG 02360 is a clear alkyd oil with good penetration properties.

**Recommended use:** As impregnation for wooden boats and hardwood above the waterline. Excellent to saturate wood before application of HEMPEL VARNISHES and PAINTS.

**Availability:** Part of European Yacht assortment. Local availability subject to confirmation.

### PHYSICAL CONSTANTS:

Shade nos/Colours: 00000/ Transparent  
Finish: Transparent (see REMARKS overleaf)  
Volume solids, %: 27 ± 1  
Theoretical spreading rate: see REMARKS overleaf  
Flash point: 38 °C [100.4 °F]  
Specific gravity: 0.8 kg/litre [7 lbs/US gallon]  
Dry to touch: 2 - 6 hour(s) at 20°C/68°F (Depending on the substrate.)  
4-12 hour(s) at 10°C/50°F (Depending on the substrate.)  
VOC content: 577 g/l [4.8 lbs/US gallon]  
*The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.*

### APPLICATION DETAILS:

Application method: Brush  
Thinner (max.vol.): HEMPEL'S THINNER 08111 (5-20%)  
Cleaning of tools: HEMPEL'S THINNER 08111  
Indicated film thickness, dry: Not relevant  
Indicated film thickness, wet: Not relevant  
Recoat interval, min: According to specification.  
Recoat interval, max: According to specification.

**Safety:** Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.



## HEMPEL'S WOOD IMPREG 02360

SURFACE PREPARATION:	<b>Untreated wood:</b> Wash the area to be treated with HEMPEL'S PRE-CLEAN 67602 as instructed and rinse with fresh water. Allow the surface to dry. Remove dust and loose material. Rough surfaces may possibly be grinded with paper no. 120, remove dust. <b>Previously treated wood:</b> Wash the area to be treated with HEMPEL'S PRE-CLEAN 67602 as instructed and rinse with fresh water. Allow the surface to dry. Remove dust and loose material.
APPLICATION CONDITIONS:	Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. Application should only take place in dry weather with temperatures above: 5°C/41°F. Avoid direct sunlight. In confined spaces provide adequate ventilation during application and drying.
PRECEDING COAT	None.
SUBSEQUENT COAT:	According to specification. Recommended systems are: HEMPEL'S CLASSIC VARNISH 01150, HEMPEL'S FAVOURITE VARNISH 01250, HEMPEL'S DURA VARNISH 02020, HEMPEL'S SATIN VARNISH 02040.
REMARKS:	<b>Spillage, remains, discarded clothes and similar should be discarded in a fireproof container due to the risk of auto ignition.</b>
Application(s)	Apply the product abundantly wet with a brush, normally 2-4 coats depending on the porosity of the wood. Allow the wood to absorb the oil for some minutes before any surplus is removed with clean lint-free rags to avoid a glossy film after drying. Depending on porosity of wooden surface, practical consumption will accordingly correspond to a spreading rate of 3-6 sq.m per litre.
Note:	<b>HEMPEL'S WOOD IMPREG 02360</b> <b>The information given in the Product Data Sheet is intended for commercial use.</b>
ISSUED BY:	HEMPEL A/S

023600000

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on [www.hempel.com](http://www.hempel.com). Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.