

Hempel's Tiger Xtra White 7103A

Product characteristics

Description

Hempel's Tiger Xtra White is a high performance, conventional, erodible antifouling providing excellent protection all season.

Recommended use

For use as an antifouling for glass fibre, wood, plywood, steel and aluminium. Ensure aluminium substrates are suitably primed. For power and sailing boats.

Features

- High mechanical strength for excellent crack resistance
- Suitable for dry-stack or continuous immersion.

Product safety

Flash point 35°C [95°F]

VOC content

Legislation	Value
EU	407 g/L [3.40 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

Product data

Product code

7103A

Standard shade* / code

Off white 10101

Gloss

Semi-flat

Volume solids

53 ± 2%

Specific gravity

1.5 kg/L [13 lb/US gal]

Reference dry film thickness

40 micron [1.6 mils]

Surface preparation

Cleanliness

- Remove salts, detergents, contaminants and marine growth by high pressure fresh water cleaning.

New build:

- Uncoated surface: Prime prepared surface with Hempel's Light Primer and apply a tiecoat of Hempel's Underwater Primer whilst the surface is still tacky.
- Uncoated surface: Prime prepared surface with Hempel's Premium Primer. Apply one coat of Hempel's Pro Tiecoat.

Maintenance and Repair

- Existing old self-polishing or traditional antifouling: Remove loose matter and contaminants by high pressure fresh water cleaning.
- Existing old hard matrix antifouling or an unknown antifouling: High pressure fresh water clean, wet abrade, remove dust.
- Clean and dry the surface.
- If previous antifouling is in general bad condition, it is recommended to remove previous coats and prime before applying antifouling.
- If the condition of previous antifouling is poor, seal with 1 coat of Hempel's Underwater Primer or Hempel's Pro Tiecoat.

* Only the White shade can be used on aluminium. Do not use other shades on aluminium.

Hempel's Tiger Xtra White 7103A

Application

Thinner

Hempel's Thinner 08080

Cleaner

Hempel's Thinner 08080
Hempel's Thinner 808 08081

Application method

Tool	Thinning max vol.
Brush/Roller	5%
Paint Pad	5%

If the vessel is regularly used at speeds above 20 knots, it is recommended to apply 3 coats of antifouling. The product can be applied by spray. Contact Hempel for more information. Keep thinning at an absolute minimum.

Film thickness

	Recommended
Dry film thickness	40 micron [1.6 mils]
Wet film thickness	75 micron [3 mils]
Theoretical spreading rate	13 m ² /L [530 sq ft/US gal]

Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Relative Humidity:

- Relative humidity must be below 85% during application.

Application remarks

- Apply 2 coats of the Antifouling paint at 40 µm dry film thickness each. Apply an additional coat around the waterline and high wear areas. Wear protective gloves/clothing and eye/face protection.
- Stir well before use.
- Copper containing antifouling must not have any electrical contact with aluminium hull and other aluminium components.
- Epoxy system for aluminium substrates must have a minimum total dry film thickness of 300 micron.

Drying and overcoating

Product compatibility

- Previous coat: Recommended products are: Hempel's Light Primer, Hempel's Underwater Primer
- Subsequent coat: None.

Drying time

Surface temperature		20°C [68°F]	10°C [50°F]	30°C [86°F]
Touch dry	min	15	30	9
Surface dry	hours	4	8	2

Determined for dry film thickness 40 micron [1.6 mils] at standard conditions, see Hempel's Explanatory Notes for details. Time to immersion: Minimum: 24 Hours 20°C ; Maximum 6 months

Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]	30°C [86°F]
Immersion				
Hempel's Tiger	Min	7 h	4 h	3 h
Xtra White 7103A	Max	Ext	Ext	Ext

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

Overcoating details

- No maximum overcoat interval, but after prolonged exposure to polluted atmosphere, remove accumulated contamination by high pressure fresh water cleaning and allow to dry before applying next coat.

Other remarks

- The surface must be clean before overcoating.

Hempel's Tiger Xtra White 7103A

Storage

Shelf life

Ambient temperature	25°C [77°F]
Product	60 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

Storage conditions

- Product must be stored according to local legislation, at 5°C [41°F] without direct sunlight and protected from rain and snow.

Additional documents

Additional information is available at the Hempel website hempel.com or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- Further information: Hempel Yacht Paint Manual and hempelyacht.com

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.