

Polycraft Pearlescent 'Cupreous Brown'

A conventional mica pearlescent pigment which has been coloured with carbon black pigment and iron oxide to create a rich, shimmering, deep brown shade with a medium particle size range of 10-60 microns and may be used on its own or tinted further with transparent dyes or pigments

Typical Properties

Particle Size Range:	10-60 microns
Mica Content:	55-65%
Iron Oxide (Fe ₂ O ₃) Content:	35-45%
Pigment Black Content:	0-1%
Density:	2.7-3.3 g/cm ³
Oil Absorption:	50-80 g/100g
pH of Aqueous Slurry:	6-10
Temperature Resistance:	≤ 200°C

Storage

Store in original packaging where possible. Store at room temperature out of direct sunlight. Shelf life 24 months.

Disclaimer

Technical Advice provided by MB Fibreglass - Either verbal, in writing or by way of trials - is given in good faith but without warranty, where proprietary rights of third parties are involved this applies also. This does not release you from the obligation to test the products supplied by us to ascertain their suitability for the intended processes and uses. The application, use, handling and processing of the products are outside of our control and therefore entirely your own responsibility