



DEV37

PROVISIONAL DATA SHEET - R&D GROUP

PRODUCT No.	UK Crystic PD9293PA
PRODUCT TYPE	Polyester Resin
APPLICATION	Casting
TYPICAL PROPERTIES: Appearance Viscosity 4500 s-1 @ 25 °C Geltime : 1 % Catalyst M @ 25 °C	Pinkish clear bit free resin 2.5 poise 9 minutes
RECOMMENDATION FOR USE	Add calcium carbonate filler to the resin at up to 40 % loading. Catalyse the resin using 1 % Catalyst M v/wt. Pour into the mould.
KNOWN HAZARDS	1. Flammable. Flashpoint below 32 °C 2. Irritant. Avoid skin and eye contact. Avoid inhalation of vapour
CAUTION NOTES	1. Flammable 2. Irritant
SAFE HANDLING INFORMATION	Refer to the MSDS. Wear gloves and eye protection.
STORAGE RECOMMENDATIONS	In the original containers below 20 °C
PACKAGING	Kegs or drums.
LABELLING	Appropriate "Unsaturated Polyester" labels.
SAMPLE SIZE	
SENDER	Sarah Carter
DATE	08/07/2003 09:26:14
<i>All information is given in good faith but without warranty. We cannot accept responsibility for any damage, loss or patent infringement resulting from the use of this information.</i>	

Scott Bader Company Limited  
Wollaston, Wellingborough, Northamptonshire NN29 7RL  
Telephone 01933 663100

Edit History: Revised by Sarah Carter at 05/08/2008 14:58:26  
Revised by Sarah Carter at 08/07/2003 09:27:28

