

## TECHNICAL DATA SHEET

**Product Reference:** 200gm 2/2 Twill Carbon Fibre

Characteristics		Nominal	Tolerance	Normative
Mass per unit area	g/m <sup>2</sup>	200	± 5%	ISO 4605
Weave		2/2Twill		ISO 2113
Width	mm	1000/2000	± 2,5%	ISO 22198
Thickness	mm	0,16	± 2,5%	ISO 5084(**)
Other information		Loomstate		

Nominal Construction		Warp		Weft	
Fibre Description		HR Carbon Fibre 3K - 200 tex		HR Carbon Fibre 3K - 200 tex	
Thread Count	ends/cm	5,0	ISO 4602	5,0	ISO 4602
Weight Distribution	g/m <sup>2</sup>	3K	100	3K	100
	%	Carbon	50%	Carbon	50%
Selvedges		Weaving style	Leno	Type of fibre	HM polyester 22 tex

(\*\*) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Technical advice provided by MB Fibreglass - Either verbal, in writing or by way of trials - is given in good faith but without warranty, where proprietary rights of third parties are involved this applies also. This does not release you from the obligation to test the products supplied by us to ascertain their suitability for the intended processes and uses. The application, use, handling and processing of the products are outside of our control and therefore entirely your own responsibility.