




# Chemlease® 15 Sealer EZ

## Mold Sealer



©2016 Chem-Trend L.P.

### Description

Chemlease® 15 Sealer EZ is a high performance sealer developed to condition and seal mold surfaces, reduce mold porosity and act as a base for new or reconditioned molds.

### Benefits

- HAPs free
- Reduces porosity problems
- Provides an excellent base coat for all types of release agents
- Compatible with fiberglass aluminum, steel, and most solid or dense surfaces
- Shortens break in time
- Reduces labor time and costs
- High temperature stability

\*HAPs are not formula constituents of this product. Standard manufacturing processes may result in trace quantities [ $<0.1\%$ ] of HAPs. Chemlease® solvent carriers contain no Class I or II registered ozone depleting substances.

### Application Instructions

#### Wiping

1. Mold surface must be thoroughly cleaned to remove all traces of wax, release agents, and other sealers. We recommend Chemlease® Mold Cleaner EZ.
2. Surface should be dry and free of contaminants.
3. Saturate clean cotton cloth (not dripping), we recommend our Chemlease® Cotton Cloth, and wipe on a smooth continuous film of no more than 0,6 meter<sup>2</sup> at a time.
4. When the film begins to evaporate at the edges approximately 15-20 seconds, wipe the surface with a second clean dry cotton cloth. Use a circular motion from the outside, working inwards until the tooling is left dry and clear. See Notes.
5. Repeat above procedures until entire mold surface has been covered. Usually only one coat is necessary on a seasoned mold (Two coats are

recommended when sealing a new or green mold. Allow 15 minutes cure time between the first and second application. Wait 1 hour after the second coat before applying the release or top coat).

6. Allow to cure for one hour before applying mold release.

### Spraying

1. Mold surface must be thoroughly cleaned to remove all traces of wax, release agents, and sealers.
2. To apply by spraying use a new, clean, hand held manual spray bottle or a clean dry air system. It is important that all containers and spray lines be thoroughly clean and dried. If container is dirty, rinse at least 2 times with an appropriate cleaner.
3. Keep spray nozzle 25 – 38 cm from mold surface and apply a smooth, thin continuous film. Do not allow to run or drip (by over applying).
4. When film begins to evaporate at edges, approximately 15-20 seconds, wipe the surface with a second clean dry cotton cloth using a circular motion from the outside, working inwards until film is left dry and clear. See Notes.
5. Repeat above procedures until the entire mold surface is covered overlapping slightly to ensure complete coverage. Usually only one coat is necessary on a seasoned mold (Two coats are recommended when sealing a new or green mold. Allow 15 minutes cure time between the first and second application. Wait one hour after the second coat before applying the release or top coat).
6. Allow to cure for one hour before applying mold release .

### Important

The recommended number of coats and cure times are a general guideline found to be more than sufficient in a broad spectrum of molding conditions. When molding products with extreme geometries or experiencing low humidity conditions in the shop, the customer may find the need to extend the cure time between coats and increase the number of coats applied to the mold. The efficiency of a



# Chemlease® 15 Sealer EZ

## Mold Sealer



©2016 Chem-Trend L.P.

release film is best determined through a combination of tape tests and experimentation.

### Troubleshooting Tips

1. Keep container closed at all times when not in use.
2. Mold must be thoroughly cleaned and dried before application. A good test to tell if the mold is clean is to use a small piece of masking tape (approximately 2,5 cm in width) on the mold surface. Sufficient resistance should be felt when removing the tape.
3. Material should be clear with no noticeable precipitate. If cloudy or milky, material is contaminated.
4. Areas of application should be well ventilated.

### Storage

Do not store above 50°C. Keep container tightly sealed to prevent evaporation and/or contamination. If stored in cold temperatures, allow to warm to room temperature before using. Do not use, if the use-by date has been exceeded.

### Packaging

Product is available in a variety of packaging. Please contact our customer service team for details.

### Safety Data

Material Safety Data Sheets are available for all Chemlease® products and should be consulted prior to use of the product.

### Further Information

Request information on our complete range of materials for this industry.

### Legal Notice

The technical information and suggestions for use contained herein is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a professional with technical experience. It does not release the customer from the obligation of performing own tests with the product selected for a specific application. While the information and suggestions are believed to be accurate and reliable, nothing stated in this bulletin is to be taken as a warranty either expressed or implied.