




Chemlease® 2185

Semi permanent release agent for composites



©2016 Chem-Trend L.P.

Description

Chemlease® 2185 is a semi permanent, room temperature curing release agent, effective for composites including polyester molding. It gives easy, multiple releases and does not require an extended cure. It is a ready-to-use liquid dispersion.

Mold Preparation/Cleaning

Because Chemlease® semi-permanent release agents polymerize on the mold surface, all traces of prior release agents, sealers and buffers/polishes must be removed from the mold.

This method will remove not only wax release agents, but also waxes, silicones and water solubles that are contained in buffing and rubbing compounds. To clean the mold following buffing, take the following steps:

1. Using liberal quantities of clean water, wipe the mold with a clean, soft, lint-free 100% cotton cloth (in the following it is called just cloth) and wipe until dry (we recommend to use our Chemlease® Cotton Cloth).
2. Soak another clean, soft, lint-free cloth with a Mold Cleaner (we recommend to use our Chemlease® Mold Cleaner EZ).
3. Apply the cleaner to the mold surface.
4. Before the cleaner dries, use a second clean cloth to wipe off the dissolved wax and other contaminants.
5. Continue steps 3 and 4 until the surface is free of wax. When all traces of prior release agent have been removed, the hand/thumb will skid, and not slip, across the mold surface.

Application

The ideal temperature of the mold for application is between 18-27°C. If Chemlease® 2185 is applied below 18°C, allow a longer time than generally recommended for room-temperature curing. If applied when the mold surface is over 27°C, curing will be faster.

1. Shake or mix well before and during use. Soak a clean cloth until it is thoroughly wet.
2. Starting at one end of the mold, wipe a generous wet film over a section of about 0,5 m².
3. Repeat until the mold is completely covered. (see note after "5" which applies to very large molds)
4. Check the treated mold for any area that appears uncoated (where haze is not present). Coat as above.

5. After the product has dried to a haze on the mold surface, polish with a cotton cloth until a high gloss is obtained. To ensure that no release agent is redeposited onto the mold, change cloth frequently.

Note: Do not allow any product to remain dry (hazed) for any longer than 30 minutes as it will become very difficult to buff out

6. Repeat steps 1-6 an additional four times for a total of five coats of Chemlease® 2185. This will allow the release agent to seal any mold pores and will give the necessary film thickness to permit multiple releases. A final polish with a clean cotton cloth will achieve a higher, Class A, gloss.

7. A cure time of 30 minutes is recommended prior to molding parts.

Touch-Up Coats

As parts are removed from the mold, abrasion will gradually wear away the release film. When slight sticking is noticed, maintain the film by applying one or two touch-up coats (as required) as described above. Molders should experience no buildup with Chemlease® 2185. Previously-applied Chemlease® does not have to be removed prior to touch-up. If the mold surface contains buildup of materials such as styrene, internal mold releases, UV absorbers, gel coats, "top coats" or other mold contaminants, clean the mold with a Chemlease® Mold Cleaner as specified under Mold Preparation/Cleaning.

Important

The recommended number of coats and cure times are a general guideline found to be more sufficient in a broad spectrum of molding conditions. When molding products with extreme geometries or experiencing low-humidity conditions in the shop, the customer may find the need to extend the cure time between coats and increase the number of coats applied to the mold. The efficiency of a release film is best determined through a combination of tape tests and experimentation.


Packaging

Product is available in a variety of packaging. Please contact our customer service team for details.



Chemlease® 2185

Semi permanent release agent for composites



©2016 Chem-Trend L.P.

Safety Data

For more information on storage, handling, hazards, etc., please request a copy of Chem-Trend's Material Safety Data Sheet, which must be consulted prior to use of this product.

Further Information

Request information on our complete range of materials for this industry.

Legal Notice

The technical information and suggestions for use contained herein is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a professional with technical experience. It does not release the customer from the obligation of performing own tests with the product selected for a specific application. While the information and suggestions are believed to be accurate and reliable, nothing stated in this bulletin is to be taken as a warranty either expressed or implied.