

# Chemlease<sup>®</sup> 41-90 EZ Semi-Permanent Release Agent

## Description

Chemlease<sup>®</sup> 41-90 EZ is a rapid curing semi-permanent mold release agent that provides multiple releases with minimal transfer to the molded part. Chemlease<sup>®</sup> 41-90 EZ a high slip version of the Chemlease<sup>®</sup> 41 family; primarily for closed molding of abrasive or low draft parts.

#### **Benefits**

- HAPs Free\*
- · High thermal stability
- · Easy to apply
- Multiple releases between applications.
- · Reduces labor time and cost

\*HAPs are not formula constituents of this product. Standard manufacturing processes may result in trace quantities [<0 .1%] of HAPs.

Chemlease® solvent carriers contain no Class I or II registered ozone depleting substances.

## **Mold Preparation**

- Clean mold surface to remove all traces of waxes, release agents and sealers.
- 2. Clean mold with Chemlease<sup>®</sup> Mold Cleaner.
- Apply the appropriate Chemlease<sup>®</sup> Sealer to new or porous molds (contact a Sales Rep or Distributor for details).

#### **Application Instructions for Base Coats**

#### To the cleaned/sealed mold surface:

- Using a wetted clean cotton cloth or fine mist spray pattern, wipe or spray on a smooth, wet, (not runny) continuous film over the entire mold surface. With a second, clean, dry cotton cloth, before film dries wipe off any excess on the mold surface.
- 2. Allow film to cure for 15 minutes.
- 3. Apply a total of 3-5 coats per the above instructions.
- 4. Allow final coat to cure for 30 minutes at room temperature.

#### Touch-Up Coats

Reapply one light coat as required and cure as for final coat.

#### **Important**

The recommended number of coats and cure times are a general guideline found to be more than sufficient in a broad spectrum of molding conditions. When molding products with extreme geometries or experiencing low-humidity conditions in the shop, the customer may find the need to extend the cure time between coats and increase the number of coats applied to the mold. The efficiency of a release film is best determined through a combination of tape tests and experimentation.

### Storage

Do not store above 49 °C/120 °F. Keep container tightly sealed to prevent evaporation and/or contamination. If stored in cold temperatures, allow to warm to room temperature before using.

#### Packaging

Chemlease<sup>®</sup> 41-90 EZ is available in a variety of package sizes. Please contact Chem-Trend customer service for details.

#### Safety Data

Safety Data Sheets are available for all Chemlease<sup>®</sup> products and should be consulted prior to use of the product.

## **Further Information**

Request information on our complete range of materials: custom-formulated release agents for polyurethane molding; tire lubes and bladder coatings; Mono-Coat® semi-permanent release coatings; aerosol formulations; mold cleaners and sealers; specialized coatings and application equipment.

While the technical information and suggestions for use contained herein are believed to be accurate and reliable, nothing stated in this bulletin is to be taken as a warranty either expressed or implied.

