
Description:	HEMPEL'S TEAK OIL 67571 is a natural oil with good penetration, enabling easy cleaning and resistance to weathering, water and dirt. Contains antimould agents.
Recommended use:	For use on new wood as well as on previously treated wood, interior and exterior, above the waterline.
Availability:	Part of European Yacht assortment. Local availability subject to confirmation.
PHYSICAL CONSTANTS:	
Shade nos/Colours:	00000/ Transparent
Finish:	Transparent
Volume solids, %:	21 ± 1
Theoretical spreading rate:	4 - 12 m ² /l [160.4 - 481.2 sq.ft./US gallon] depending on porosity
Flash point:	62 °C [143.6 °F]
Specific gravity:	0.8 kg/litre [7 lbs/US gallon]
Dry to touch:	8 hour(s) 20 micron/0.8 mils 16 hour(s) 10°C/50°F
VOC content:	618 g/l [5.1 lbs/US gallon]
Shelf life:	5 years 25°C/77°F
	<i>The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.</i>
APPLICATION DETAILS:	
Application method:	Brush / Roller
Thinner (max.vol.):	Do not dilute.
Cleaning of tools:	HEMPEL'S THINNER 808 (No 3) 08081
Indicated film thickness, dry:	Not relevant.
Indicated film thickness, wet:	Not relevant.
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.

SURFACE PREPARATION:	Preparation: Always ensure all surfaces are clean, oil free and dry. Clean with suitable detergent. Rinse the surface with fresh water. Allow to dry. New wood: Clean with HEMPEL'S TEAK CLEANER 67543. Rough surfaces may be sanded. Remove dust and loose material. Previously treated wood: Remove dust and loose material.
PRODUCT APPLICATION:	Method: Apply one saturation coat directly onto the surface. Allow the oil to absorb into the wood. Any surplus product should be removed with clean cloths to avoid a glossy film after drying. For maintenance, apply a thin coat of the product.. Remove surplus material before it dries. Not suited for varnished or painted wood. May be used to overcoat HEMPEL'S TEAK COLOUR RESTORER 67462 on areas of high usage.
APPLICATION CONDITIONS :	The surface must be completely clean and dry at the time of application and its temperature must be above the dew point to avoid condensation. The moisture content in the wood should not exceed: 16%. Do not apply in direct sunlight. In confined spaces provide adequate ventilation during application and drying.
RECOMMENDED DETERGENT :	HEMPEL'S PRE-CLEAN 67602
PRECEDING COAT:	HEMPEL'S TEAK CLEANER 67543
SUBSEQUENT COAT:	None.
REMARKS:	Spillage, remaining oil, discarded cloths and similar should be discarded in a fireproof container due to the risk of auto ignition.
Stirring:	Stir product well before use.
Storage Conditions:	Exposure to air and temperature variances should be avoided. Avoid direct sunlight. Keep containers tightly sealed. Store at temperatures: 5°C/41°F - 35°C/95°F.
Overcoating:	Not relevant
Note:	HEMPEL'S TEAK OIL 67571
ISSUED BY:	HEMPEL A/S 6757100000

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.