

## Polycraft Pearlescent 'Light Green'

A conventional mica pearlescent to which has been applied a coating containing phthalocyanine green pigment thus creating shimmering green effect pigment with a medium particle size range of 10-60 microns and is semi-transparent.

### Typical Properties

Particle Size Range:	10-60 microns
Mica Content:	81-84%
Titanium Dioxide (TiO <sub>2</sub> ) Content:	10-13%
Tin Oxide (SnO <sub>2</sub> ) Content:	0-1%
Pigment Green 7 Content:	0-5%
Density:	2.7-3.0 g/cm <sup>3</sup>
Oil Absorption:	70-85 g/100g
pH of Aqueous Slurry:	4-6
Temperature Resistance:	≤ 200°C

### Storage

Store in original packaging where possible. Store at room temperature out of direct sunlight. Shelf life 24 months.

### Disclaimer

Technical Advice provided by MB Fibreglass - Either verbal, in writing or by way of trials - is given in good faith but without warranty, where proprietary rights of third parties are involved this applies also. This does not release you from the obligation to test the products supplied by us to ascertain their suitability for the intended processes and uses. The application, use, handling and processing of the products are outside of our control and therefore entirely your own responsibility